

**SPECIFICATION FOR 62.5/125 MULTIMODE OPTICAL FIBRE: ISO/IEC 11801 & IEC 60793-2-10 Type A1b SPECIFICATION**

**OPTICAL PROPERTIES**

Attenuation	@ 850 nm @ 1300 nm	≤ 3.2 dB/km ≤ 0.8 dB/km
Overfilled Modal Bandwidth	@ 850 nm @ 1300 nm	≥ 200 MHz.km ≥ 500 MHz.km
Numerical Aperture		0.275 ± 0.015
Attenuation Uniformity	Point or Step Defects Extended variations	≤ 0.2 dB ≤ 0.2 dB
Group Index of Refraction	(Typical) 850 nm 1300 nm	1.495 1.490

**GEOMETRICAL PROPERTIES**

Core		62.5 ± 2 µm
Core Non-Circularity		≤ 5.0 %
Core / Cladding Concentricity Error		≤ 1 µm
Cladding Diameter		125.0 ± 1.0 µm
Cladding Non-Circularity		≤ 0.7 %
Coating Diameter		245 ± 10 µm
Coating Concentricity Error		≤ 12.5 µm
Coating Non-Circularity		≤ 6 %

**MECHANICAL PROPERTIES**

Proof Test Level		≥ 0.69 GPa / ≥ 1.0 %
------------------	--	----------------------